



TUBALL™

MATRIX

202

TECHNICAL DATA SHEET

CONCENTRATE FOR PVC, POLYURETHANE AND PHENOLIC RESINS

TUBALL™ MATRIX 202 is a concentrate based on TUBALL™ graphene nanotubes specifically designed to provide superior electrical conductivity to PVC resins and solvent-free polyurethane and phenolic systems while retaining mechanical properties and minimally impacting the host matrix. TUBALL™ MATRIX 202 is available in flakes with a pasty texture form.

TUBALL™ is a unique graphene nanotube additive from OCSiAl that provides electrical conductivity at ultra-low dosage with minimal impact on the rheological and mechanical properties of the host matrix.

APPLICATIONS

- Electrostatic dissipative coatings;
- Anti-static PVC;
- Anti-static composite materials and compounds;
- Other applications where electrical conductivity is required.

BENEFITS

- TUBALL™ MATRIX only requires an ultra-low dosage starting from just 0.1 wt.%;
- Allows production of conductive parts that retain bright colors;
- Maintains or even increases mechanical strength;
- Ensures permanent and uniform electrical conductivity without “hot spots”;
- Without a significant increase in viscosity or density of the host material.

PROPERTIES


CONCENTRATE CARRIER	FATTY CARBOXYLIC ACID ESTER DERIVATIVES	
PROPERTY	TEST METHOD	VALUE
Flash point	ASTM D3278	224°C
Density at 25°C	ASTM D4052	0.97 g/ml
Hydroxyl value	ASTM E1899-08	<20 mg KOH/g
Moisture content	OCSiAl internal method	≤1 wt.%

TUBALL™ MATRIX 202 may contain particles up to 500 µm in size; the mass concentration of such inclusions does not exceed 0.04%.

TYPICAL ADDITION RATE

Depending on the characteristics of the dilution polymer and the processing conditions, the loading range of TUBALL™ MATRIX 202 for anti-static or dissipative applications can be as low as 0.1–3.0 wt.%. The exact loading level depends on the required performance, resin characteristics, processing conditions and presence of other ingredients.

An example of a percolation curve, obtained by compounding TUBALL™ MATRIX 202 in PVC resin, is shown in the figure below. The dilution of the concentrate in neat PVC resin was performed using a mechanical overhead stirrer and the surface resistivity was measured on compression-molded samples.



DILUTION

In order to obtain a high-quality TUBALL™ MATRIX dispersion, OCSiAl recommends that close attention be paid to the dilution procedure. Refer to the Processing Guidelines for detailed information.

PACKAGING

OCSiAl provides TUBALL™ MATRIX 202 samples in plastic containers (50 g concentrate). Industrial volumes are available in different packaging up to 50 kg.

STORAGE AND TRANSPORTATION

The product is stable in unopened original packaging when stored in dry ventilated conditions. The recommended storage life is up to 12 months when stored as directed.

SAFETY

To ensure safe handling, the appropriate safety regulations should be observed. OCSiAl recommends that every user should be able to apply the safe handling procedures necessary for the user's applications before any handling or manufacturing takes place. A Safety Data Sheet outlining the hazards and handling methods for TUBALL™ MATRIX 202 is available.

WARRANTIES AND DISCLAIMER

The Products correspond to the chemical composition indicated in the Technical Data Sheet and the Safety Data Sheet supplied with the Product. The information contained in this document (Information) is based on trials carried out by OCSiAl and may contain inaccuracies or errors that could cause injury, loss or damage.

OCSiAl gives no further warranty and makes no further representation regarding the Products and/or the accuracy of Information and/or suggestions for any particular use of the Products or Information, or that suggested use will not infringe any patent. The Products and Information are supplied on an “as is” basis. These express provisions are in place for all warranties, representations, conditions, terms, undertakings and obligations implied by statute, common law, custom, trade usage, course of dealing or otherwise (including implied undertakings of satisfactory quality, conformity with description, fitness for purpose and reasonable skill and care), all of which are hereby excluded to the maximum extent permitted by applicable law.

CONTACT INFORMATION

ASIA		EUROPE		NORTH & SOUTH AMERICA
KOREA 11F, 254-8 Gongdeok-dong, Mapo-gu, Seoul 04212, Korea +82 32 260 0407 asiapacific@ocsial.com	CHINA #2004, 20th floor, Tower B, Da Chong Business Centre, Yue Hai Street, Nanshan District, Shenzhen, Guangdong, China +86 755 867 00059 Ground floor, Unit 4, Building 7, No.160, Basheng Road, Pudong district, Shanghai, China +86 135 9012 5295 china@ocsial.com	JAPAN Tokyo, Japan 070-1421-0331 japan@ocsial.com	LUXEMBOURG 1 Rue de la Poudrerie, L-3364, Leudelange, Grand-Duché de Luxembourg +352 27990373 europe@ocsial.com	USA 950 Taylor Station Road, Suite #W, Gahanna, OH 43230, USA +1 415 906 5271 usa@ocsial.com
HONG KONG Room 1102, 11/F, Lippo Sun Plaza, 28, Canton Road, Tsim Sha Tsui, Kowloon, Hong Kong +852 3575 3946		INDIA Vimal intertrade PVT Ltd, Shivam centrium, Sahar road, Koldongri, Andheri East, Mumbai, 400 069, India + 91 22 6288 4200 india@ocsial.com		